إستهلال (وقل ربً زدني عِلْمًا) سورة طه – الآية 114

Dedication

This work is dedicated to my

parents

brothers and sisters

Acknowledgment

First and foremost, praise to almighty Allah, who give me the strength and patience to conduct this research

I wish to express my gratitude and thanks to Prof. Mohammed Elmubark
Osman for his guidance, suggestions, encouragement and support throughout the
period of study.

Thanks are also due to the Sudanese Standards and Metrology Organization for technical support.

Abstract

In this work formulation of Henna gel and cream were achieved. A blend of Gum Arabic and Karaya Gum was used along with Henna extract to formulate a paste for cosmetic and natural uses.

The physical properties of the prepared Henna gel and cream were investigated and adjusted to improve their quality.

The henna cream was prepared using Henna solution 5.75 % and Karaya gum 6.3%, the physical properties of the cream were determined, pH was equal to 4.55 and moisture was equal to 63.91%.

The gel was prepared using Henna solution 5.75 %, Karaya gum 6.3% and gum arabic13.5%, the physical properties of the gel were determined, pH was equal to 4.48 and moisture was equal to 65.88%

المستخلص

في هذا العمل, تم تكوين هلام وكريم الحنة, تم استخدام مزيج من الصمغ العربي وصمغ الكرايا بالإضافة إلى مستخلص الحنة لتكوين معجون يصلح للإستخدامات التجميلية والطبيعية

تمت در اسة الخصائص الفيزيائية لهلام وكريم الحنة و مواءمتها لرفع مستوى جودتهما.

تم تحضير كريم الحنة باستخدام محلول الحنة % 5.75 وصمغ الكرايا % 6.3 وبدر اسة الخواص الفيزيائية للكريم وجد ان الرقم الهيدر وجينى % 6.5 والرطوبة %

تم تحضير الهلام باستخدام محلول الحنة % 5.75 وصيمغ الكرايا %6.3 والصيمغ العربي 3.5% وبدر اسية الخواص الفيزيائية للهلام وجد ان الرقم الهيدروجيني 4.48 والرطوبة65.88%

Table of Contents

Content	Page
إستهلال	Ι
Dedication	II
Acknowledgment	III
Abstract	IV
المستخلص	V
Table of Contents	VII
List of Tables	VIII
List of Figures	IX
Chapter One	
Introduction	
1.Introduction	1
1.1. Acacia gums	1
1.1.1. Botanical Classification	2
1.1.2. Botanical Description	2
1.1.3. Chemical Constituents	4
1.1.4. Chemical Structure	5
1.1.5. Properties	6
1.1.6. Specifications	7
1.1.7. Applications of Gum Arabic	7
1.2. Karaya Gum	9
1.2.1. Botanical Classification	9
1.2.2. Botanical Description	10
1.2.3. Chemical Constituents	11
1.2.4. Chemical structure	12
1.2.5. Properties	12
1.2.6. Specifications	13
1.2.7. Applications of Karaya Gum	13
1.3. Lawsonia inermis (Henna)	14
1.3.1. Botanical Classification	14
1.3.2. Botanical Description	14
1.3.3. Chemical Constituents	17
1.3.4. Chemical structure	18
1.3.5. Applications of Henna	18
1.3.6. Other applications of Henna	19
1.4. Objectives	20
Chapter Two	

Materials and Methods		
2.1. Materials	21	
2.2. Methods	21	
2.2.1. Moisture Measurement (for Karaya Gum, Lawsonia inermis	21	
solution and Gum Arabic)		
2.2.2. Preparation of Henna solution	21	
2.2.3. Formulation of cream	21	
2.2.4. Formulation of gel	22	
2.2.5. pH Measurement	22	
2.2.6. Moisture Measurement (for cream and Gel)	22	
Chapter Three		
3.1. Results and discussion	23	
3.2. Conclusion	24	
3.3. Recommendation	25	
References	26	
Appendix	30	

List of Tables		
Table	Page	
	No.	
Table (1-1): Analytical data for the gum obtained from Acacia Senegal	6	
Table (1-2): Mineral composition of Karaya gum (μg/g) from Blue	12	
Nile and Kordofan regions		
Table (3-1): Physical property (moisture): Gum Arabic, Karaya gum,	25	
Henna powder, Cream and Gel		
Table (3-2): Physical property (pH): of the cream and gel.	25	

List of Figures	
Figure	Page
	No.
Figure (1-1): African Gum Arabic belt	1
Figure (1-2): Gum Arabic in acacia tree	3
Figure (1-3) : Illustration of a possible structural fragment of <i>A. senegal</i>	5
gum	
Figure (1-4): Putative molecular structure for A.senegal gum	5
Figure (1-5): Karaya Gum	11
Figure (1-6): Chemical structure of karaya gum.	12
Figure (1-7): Henna tree	20
Figure (1-8): Henna	20
Figure (1-9): Structure of lawsone	21